

In the Specification:

Please make the following changes in the paragraph between lines 18 and 19 on page 4, of the U.S. Specification:

This object is achieved by ~~the glass described in patent claim 1~~ borosilicate glass having a composition, in percent by weight based on oxide content of:

<u>SiO₂</u>	<u>70 - 77</u>
<u>B₂O₃</u>	<u>6 - < 11.5</u>
<u>Al₂O₃</u>	<u>4 - 8.5</u>
<u>Li₂O</u>	<u>0.15 - 2</u>
<u>Na₂O</u>	<u>4.5 - 9.5</u>
<u>K₂O</u>	<u>0 - 5</u>
<u>with Li₂O + Na₂O + K₂O</u>	<u>5 - 11</u>
<u>MgO</u>	<u>0 - 2</u>
<u>CaO</u>	<u>0 - 2.5</u>
<u>with MgO + CaO</u>	<u>0 - 3</u>
<u>ZrO₂</u>	<u>0 - < 0.5</u>
<u>CeO₂</u>	<u>0 - 1,</u>

and optionally at least one standard refining agent in an amount sufficient for refining.